

# Hempacore One

## Product characteristics

### Description

Hempacore One is a one component, solvent-borne, physically drying intumescent coating for passive fire protection of structural steel against cellulosic fires in a wide range of fire durations. It is suitable for in-shop and on-site applications, interior and exterior use.

### Recommended use

As intumescent fire protection for structural steel in interior and exterior conditions, up to Type X (EAD350402-00-1106 / EN 16623) and C4 conditions (ISO 12944-2). Suitable for I section beams, H columns, hollow sections and cellular beams.

As a repair and touch-up coating for damaged areas of freshly applied Hempacore One .

### Certificates / Approvals

- CE marked product with European Technical Assessment (ETA) ETA 12/0581. Up to 180 minutes.
- Third-party certified by Certifire certification Certifire CF 5146. Up to 120 minutes.
- Third party certified by Applus; Fire Safety Mark ApplusFire APF - 1779. Up to 180 minutes.
- Assessed according to GOST R53295, Russian Fire test for structural steel
- Tested and approved for Chinese fire test standard GB14907 (Fire resistive coating for steel structure). Up to 2 hours.
- UL-certified to applicable European (EN) standards and UL-EU Mark service requirements. Certificate UL-EU-00832-CPR.
- Assessed according to EN 13381-9, fire resistance of structural steel (cellular beams)
- Assessed according to BS 476-21, Fire resistance of structural steel Up to 120 minutes.
- Complies with the European Fire Standard EN 13501-1, reaction to fire classification, when used as part of a predefined paint system.

### Features

- One product for most common steel sections to reduce complexity application and specification.
- Wide range of fire durations (from 30 to 180 min) and massivities with competitive loadings.
- It has been approved and 3rd party certified according to EN 13381-8, BS-476 20/21, AS 4100 and GB 14907:2018. It has ETA with CE mark, Certifire and ApplusFire certificate. Complies with TR EAEU 043/2017 and assessed according to GOST R 53295.
- Dries fast to a smooth defect-free surface to provide excellent cosmetic finish to steel.
- Can be applied up to 1500 micron [60 mils] dry film thickness per coat, thus providing the required protection in less coats if needed.
- 12 months weather resistant without topcoat provided that coating is sufficiently dried, applied according the Application Instructions and not exposed to condensation, running or pooling water.
- Environmental Product Declaration with third-party certification available (Type III EPD, acc. to ISO 14025, EN 15804). Product can contribute to EPD credits for LEED and BREEAM projects.
- Complies with EU Directive 2004/42/EC, The Paints Directive on the limitation of volatile organic compounds: subcategory i.

## Product safety

**Flash point** 23°C [73°F]

### VOC content

| Legislation     | Value                    |
|-----------------|--------------------------|
| EU              | 320 g/L [2.67 lb/US gal] |
| US (coatings)   | 345 g/L [2.88 lb/US gal] |
| US (regulatory) | 345 g/L [2.88 lb/US gal] |
| China           | 345 g/L [2.88 lb/US gal] |

According to ISO 11890-1. \*EU Directive 2004/42/CE. According to specific legislation, see details in the Explanatory Notes available at Hempel website, [hempel.com](http://hempel.com) or at your local Hempel website.

### Handling

Handle with care. Before and during use, observe safety labels on packaging and paint containers and follow all local and national safety regulations. Always consult Hempel's Safety Data Sheet for this product along with the Product Data Sheet.

For professional use only.

# Hempacore One

## Product data

**Product code**  
43600

**Standard shade / code**  
White 10000

**Gloss**  
Flat

**Volume solids**  
75 ± 3%

**Specific gravity**  
1.3 kg/L [11 lb/US gal]

## Surface preparation

### Cleanliness

- Remove salts, detergents and other contaminants by high pressure fresh water cleaning.
- Abrasive blasting to min. Sa 2½ (ISO 8501-1) / SP 10 (SSPC).
- Zinc coated surfaces: use non-metallic blast media (corundum, garnet, etc.).
- Use approved primer.
- Remove oil, grease and other contaminants by suitable detergent cleaning.
- Remove dust, blast media and loose materials.
- The surface must be dry and clean prior to application.
- For approved substrates other than Carbon Steel, the substrate may require other surface preparations, consult Hempel's application instructions for detailed information.
- Minor areas can be cleaned by power tool to St 3 provided the surface is roughened and not polished.
- Consult Hempel's separate Surface Preparation Guidelines for more details.

### Maintenance and Repair

- Minor areas may be hand or power tool cleaned instead of abrasive blasting.

Consult Hempel's separate Surface Preparation Guidelines for more details.

## Application

### Thinner

Not Recommended

### Cleaner

Hempel's Thinner 08080  
Hempel's Tool Cleaner 99610

### Application method

| Tool          | Application parameters  |
|---------------|---|
| Airless spray | Nozzle pressure: 200 bar [2900 psi]<br>Nozzle orifice: 0.017-0.023" |

If brush or roller application is used, more coats will be necessary to achieve the specified dry film thickness. In general, thinning is not recommended. Spray data are indicative and subject to adjustment. Pressure is for a material temperature of 20°C [68°F].

### Film thickness

The film thickness is dependent on the required fire resistance as well as the massivity factor (Hp/A) of the steel element. Please contact your local Hempel representative. The maximum thickness per coat is 1500 micron [60 mils] Dry Film Thickness equivalent to 2000 micron [80 mils] Wet Film Thickness. Please consult the Application Instruction for more detailed information.

### Application conditions

- To avoid condensation, apply on a clean and dry surface with a temperature that is at least 3°C [5°F] above the dew point.

### Application remarks

- Stir well before use.

## Drying and overcoating

### Product compatibility

- Previous coat: According to Hempel's Specification. Only Hempel approved primer. Consult Hempel representative for information on approved primers.
- Subsequent coat: According to Hempel's Specification. A selection of approved topcoats is available. Consult Hempel representative for information on approved topcoats.

# Hempacore One

## Overcoating details

- Please consult the specific Drying time and Overcoating details for this product.
- Consult Hempel for specific details
- A topcoat cannot be applied before the specified intumescent thickness has been achieved and the coating is sufficiently dry. Consult Hempel representative for more detailed information.

## Storage

### Shelf life

| Ambient temperature | 25°C<br>[77°F] |
|---------------------|----------------|
| Product             | 15 months      |

Shelf life from date of production, when stored in original, unopened containers. Thereafter, the product quality must be re-inspected. Storage at elevated temperatures may reduce shelf life. For advice, please consult Hempel.

### Storage conditions

- In case shelf life is exceeded, the product must be re-evaluated before use. Please contact a Hempel representative.

## Additional documents

Additional information is available at the Hempel website <https://www.hempel.com/service-and-support/technical-guidelines> or at your local Hempel website:

- Explanatory Notes for Product Data Sheet.
- Application methods.
- Application Instruction for this product.
- Drying time and Overcoating Intervals for this product.
- List of approved primers and topcoats

This Product Data Sheet ("PDS") relates to the supplied product ("Product") and is subject to updating from time-to-time. Accordingly, the buyer/applicator should have regard to the PDS supplied together with the relevant batch of the Product (and not an earlier version). In addition to the PDS, the buyer/applicator may receive some or all of the following specifications, statements and/or guidelines as listed below or as are available from the Hempel website under 'Products' at [www.hempel.com](http://www.hempel.com) (the "Additional documents"):

| No. | Document description   | Location/comments   |
|-----|--|---|
| 1.  | Technical Statement  | One-off specific advice provided on request for specific projects   |
| 2.  | Specification  | Only issued for specific projects   |
| 3.  | PDS  | This document   |
| 4.  | Explanatory Notes to the PDS   | Available at <a href="http://www.hempel.com">www.hempel.com</a> and contain relevant information about the Product testing parameters |
| 5.  | Application Instruction  | Where available, at <a href="http://www.hempel.com">www.hempel.com</a>  |
| 6.  | Generic technical guidelines (e.g. on application and surface preparation) | Where available, at <a href="http://www.hempel.com">www.hempel.com</a>  |

In the event of a conflict of information between the PDS and the Additional documents, the order of priority of information shall be in the order as set out above. In such event you should also contact your representative at Hempel for clarification. Furthermore, the buyer/applicator must have full regard to the relevant Safety Data Sheet provided with each Product and which can also be downloaded from [www.hempel.com](http://www.hempel.com).

Hempel shall not be liable for defects where the application of the Product has not been made fully in accordance with the recommendations and requirements set out in the relevant PDS and the Additional Documents. The information and terms of this disclaimer apply to this PDS, the Additional documents and any other documents supplied by Hempel in respect of the Product. In addition, the Product is supplied and all technical assistance is given subject to Hempel's General Conditions of Sale, Delivery and Service, unless otherwise expressly agreed in writing.